

## CAM-Spheres 300-XG-FGR Specification

Version 3.0 - June 2022

**Product:** White alumino-silicate cenospheres

**Chemical composition:**

	Typical Value	Range
Al <sub>2</sub> O <sub>3</sub>	35.0%	32 - 37%
SiO <sub>2</sub>	56.5%	54 - 60%
Fe <sub>2</sub> O <sub>3</sub>	1.6%	1.5 - 3.5%
MnO	0.2%	0.1 - 0.5%
MgO	0.6%	0.5 - 1.0%
Na <sub>2</sub> O	0.5%	0.3 - 1.0%
TiO <sub>2</sub>	1.0%	0.5 - 2.0%
CaO	1.3%	0.8 - 2.0%

**Physical properties:**

	Unit	Range
Bulk weight	g/cm <sup>3</sup>	0.36 - 0.46
Specific gravity	g/cm <sup>3</sup>	0.75 - 0.95
Melting point	°C	1525 - 1650
Sinker	%	< 6
Moisture content	%	< 0.3
Color		white
pH		7.0 - 9.9

**Particle size distribution:**

Size in µm	Average, %	Min/Max. in %
> 500	0	0
300 - 500	1	5
150 - 300	80	≥ 75
63 - 150	15	≤ 25
< 63	5	20

**Packaging:**

- Big bags of 500kg with plastic liner, 2 bags stacked per pallet
- Paper bags of 20kg net, on pallets

The above values represent typical property values of the product and are accurate to the best of our knowledge.